

## THE BISHOP MATERIALS LABORATORY

100 Clemson Research Blvd. Anderson, SC 29625 (864) 656-1094 Fax: (864) 656-1095 www.bishopmaterialslab.com



Results of Tests on Brick conducted in accordance with ASTM C67-12 Standard Method for Sampling and

Testing Brick and Structural Clay Tile

04/19/2013

Name: Glen-Gery Corporation

433 S. Pottsville Pike

Shoemakersville, PA 19555

Phone: 610-562-3076

Fax: 610-562-2084 Plant:

GGMA-0788

Report Number:

Mid-Atlantic 02/17/2012

Sampled Date: Lot:

Product Code:

72502200

**Mid-Atlantic Shale Molded Thin Brick** Sample Description:

							Test Date
Absorption	1	2	3	4	5	Average	
24 Hour Submersion in Cold Water (%)	6.13	7.23	6.40	6.16	6.17	6.42	03/15/2012
5 Hour Submersion in Boiling Water (%)	10.96	11.91	11.14	10.94	11.00	11.19	
Saturation Coefficient (Ratio of 24H to 5H)	0.56	0.61	0.57	0.56	0.56	0.57	
Efflorescence	11	12	13	14	15		
	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		03/01/2012

The brick represented by the test results shown here comply with the standards listed below:

ASTM C 1088 - 12 Standard Specification for thin Veneer brick Units Made From Clay or Shale

Grade: Exterior, Interior

John Sanders, Ph.D., PE, Director

Gary W. Parker, Laboratory Supervisor

Lab Reference: 4291.6130