

Technical Data Sheet

KF Series

Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Antique		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Heritage S		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Heritage SWB		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Mohawk		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Old Mystic		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Rocky Mountain		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Sandford		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25
Shrewsbury		Modular	ASTM C216	SW	FBS	>5,000	<8	<10	<30	<25

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024









Size	Width	Height	Length	Weight	Brick per Cube	Brick per Sq Ft
Modular	3-5/8"	2-1/4"	7-5/8"	4.3	530	6.86

Note: products are also available as Thin Brick, see Thin Brick Technical Data Sheet.

Technical Data Sheet

KF Series -- Thin Brick
Mid-Atlantic Plant



Product Name	Swatch	Size	Standard	Durability Class (Grade)	Dimensional Variation (Type)	Compressive Strength (psi)	24-hr Cold Water Absorption (%)	5-hr Boil Absorption (%)	IRA (g/min per 30in ²)	Core Volume (%)
Antique Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Heritage S Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Heritage SWB Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Mohawk Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Old Mystic Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Rocky Mountain Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Sandford Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A
Shrewsbury Thin Brick		Modular	ASTM C1088	Exterior	TBS	N/A	<8	<10	N/A	N/A

This data represents average results. If specific test results are required, sample should be taken from current production lots. U.S. STANDARD TEST METHODS (ASTM C67) ARE USED AS APPLICABLE, UNLESS OTHERWISE NOTED. ©2024

Size	Thickness	Width	Height	Length	Weight	Brick per Pack	Brick per Pallet	Brick per Sq Ft
Modular Thin Brick Flat	3/4"	3/4"	2-1/4"	7-5/8"	1.1	30	2700	6.86
Modular Thin Brick Corner	3/4"	3-5/8"	2-1/4"	7-5/8"	1.4	12	1080	4.5/LF

Note: products are also available as Full Brick, see Full Brick Technical Data Sheet.